




# ZENIT

## MOTIV COLLECTION

<b>CONSTRUCTION STRUCTURE STRUKTUR STRUCTUUR</b>	Tufting 1/10" loop pile Tufté 1/10" loop pile Getuftet 1/10" loop pile Getuft 1/10" loop pile	<b>FASTNESS TO LIGHT SOLIDITÉ A LA LUMIÈRE LICHTECHTHEIT LICHTECHTHEID</b>	EN ISO 105-B02 ≥ 5-6
<b>PILE MATERIAL COMPOSITION DU VELOURS POLMATERIAL POOLMATERIAAL</b>	100% PP	<b>COLOUR FASTNESS TO WATER SOLIDITÉ À L'EAU WASSERECHTHEIT WATERECHTHEID</b>	EN ISO 105-E01 ≥ 4-5
<b>SECONDARY BACKING DOSSIER RÜCKEN TAPIJTRUG</b>	Bitumen back Min. 70% recycled content	<b>FIRE RESISTANCE COMPORTEMENT AU FEU BRENNVERHALTEN BRANDGEDRAG</b>	EN 13501-1 C <sub>FL-s1</sub>
<b>PILE WEIGHT POIDS DU VELOURS POLEINSATZGEWICHT POOLGEWICHT</b>	± 550 gr/m <sup>2</sup>	<b>SIZE DIMENSION ABMESSUNG AFMETING</b>	50 X 50 cm
<b>TOTAL WEIGHT POIDS TOTAL GESAMTGEWICHT TOTAAL GEWICHT</b>	± 4.300 gr/m <sup>2</sup>	<b>PACKAGING EMBALLAGE VERPACKUNG VERPAKKING</b>	5 m <sup>2</sup> /b 20 b/p
<b>PILE THICKNESS EPAISSEUR DU VELOURS POLDICKE POOLDIKTE</b>	± 4,0 mm		
<b>TOTAL THICKNESS EPAISSEUR TOTALE GESAMTDICKE TOTALE DIKTE</b>	± 7,0 mm		
<b>TUFT DENSITY NOMBRE DE POINTS NOPPENZAHL AANTAL PUNTEN</b>	± 212.760/m <sup>2</sup>		
<b>PRODIS / GUT</b>	E306FDDE		
<b>CLASSIFICATION CLASSEMENT KLASSIFIKATION CLASSIFICATIE</b>	EN 1307 22 - LC1		

01/23 All rights reserved to alter technical specification  
Sous réserve de modifications techniques  
Unter Vorbehalt von technischen Änderungen  
Onder voorbehoud van wijzingen van de technische specificaties.



EN 14041 
16
ITC CO BV Kanegemstraat 15 - BE 8700 Tielt
DOP: 1010#BIOACL
Textile Floor Covering EN 1307 Notified body 0493
