

LINEATIONS

MOTIV COLLECTION

CONSTRUCTION STRUCTURE STRUKTUR STRUCTUUR	Tufting 1/10" loop pile Tufté 1/10" loop pile Getuftet 1/10" loop pile Getuft 1/10" loop pile	FASTNESS TO LIGHT SOLIDITÉ A LA LUMIÈRE LICHTECHTHEIT LICHTECHTHEID	EN ISO 105-B02 ≥ 5-6
PILE MATERIAL COMPOSITION DU VELOURS POLMATERIAL POOLMATERIAAL	100% PP	COLOUR FASTNESS TO WATER SOLIDITÉ À L'EAU WASSERECHTHEIT WATERECHTHEID	EN ISO 105-E01 ≥ 4-5
SECONDARY BACKING DOSSIER RÜCKEN TAPIJTRUG	Bitumen back Min. 70% recycled content	FIRE RESISTANCE COMPORTEMENT AU FEU BRENNVERHALTEN BRANDGEDRAG	EN 13501-1 C _{FL} -s1
PILE WEIGHT POIDS DU VELOURS POLEINSATZGEWICHT POOLGEWICHT	± 550 gr/m ²	SIZE DIMENSION ABMESSUNG AFMETING	50 X 50 cm
TOTAL WEIGHT POIDS TOTAL GESAMTGEWICHT TOTAAL GEWICHT	± 4.300 gr/m ²	PACKAGING EMBALLAGE VERPACKUNG VERPAKKING	5 m ² /b 20 b/p
PILE THICKNESS EPAISSEUR DU VELOURS POLDICKE POOLDIKTE	± 4,0 mm		
TOTAL THICKNESS EPAISSEUR TOTALE GESAMTDICKE TOTALE DIKTE	± 7,0 mm		
TUFT DENSITY NOMBRE DE POINTS NOPPENZAHL AANTAL PUNTEN	± 189.120/m ²		
PRODIS / GUT	E306FDDE		
CLASSIFICATION CLASSEMENT KLASSIFIKATION CLASSIFICATIE	EN 1307 22 - LC1		

01/23 All rights reserved to alter technical specification
Sous réserve de modifications techniques
Unter Vorbehalt von technischen Änderungen
Onder voorbehoud van wijzingen van de technische specificaties.

