

PRIMA

BOHEMIA COLLECTION

CONSTRUCTION STRUCTURE STRUKTUR STRUCTUUR	Tufting 5/16" loop pile Tufté 5/16" loop pile Getuftet 5/16" loop pile Getuft 5/16" loop pile	FASTNESS TO LIGHT SOLIDITÉ A LA LUMIÈRE LICHTECHTHEIT LICHTECHTHEID	EN ISO 105-B02 ≥ 5-6
PILE MATERIAL COMPOSITION DU VELOURS POLMATERIAL POOLMATERIAAL	100% PP	COLOUR FASTNESS TO WATER SOLIDITÉ À L'EAU WASSERECHTHEIT WATERECHTHEID	EN ISO 105-E01 ≥ 4-5
SECONDARY BACKING DOSSIER RÜCKEN TAPIJTRUG	Texflor® back	FIRE RESISTANCE COMPORTEMENT AU FEU BRENNVERHALTEN BRANDGEDRAG	EN 13501-1 E _{FL} -s1
PILE WEIGHT POIDS DU VELOURS POLEINSATZGEWICHT POOLGEWICHT	± 610 gr/m ²	WIDTH LARGEUR BREITE BREEDTE	EN ISO 3018 ca. 400,500 cm
TOTAL WEIGHT POIDS TOTAL GESAMTGEWICHT TOTAAL GEWICHT	± 1.535 gr/m ²		
PILE THICKNESS EPAISSEUR DU VELOURS POLDICKE POOLDIKTE	± 6 mm		
TOTAL THICKNESS EPAISSEUR TOTALE GESAMTDICKE TOTAAL DIKTE	± 8 mm		
TUFT DENSITY NOMBRE DE POINTS NOPPENZAHL AANTAL PUNTEN	± 43.750/m ²		
PRODIS / GUT	8DFDFFE1		
CLASSIFICATION CLASSEMENT KLASSIFIKATION CLASSIFICATIE	EN 1307 22 - LC1		

01/22 All rights reserved to alter technical specification
Sous réserve de modifications techniques
Unter Vorbehalt von technischen Änderungen
Onder voorbehoud van wijzingen van de technische specificaties.



EN 14041

12
ITC CO BV Kanegemstraat 15 - BE 8700 Tielt
DOP: 1010#BA0AEL
Textile Floor Covering EN 1307
